


# **Aceox**<sup>®</sup> **TMCH PRODUCT DATA SHEET** 1,1-Di-(tertial butylperoxy)-3,3,5-trimethylcyclohexane

Issued Date 2009/05/10

### Description

ACEOX TMCH is a low volatility , yellowish liquid peroxy ketal peroxide.

#### **Chemical structure**



## Specifications

Typical Property	Unit	Standard
Color	hazen	60 max
Assay	%	88-90
Active oxygen	%	9.30-9.52
Fe	%	0.0005 max
TBHP	%	≤ 0.1

## Application

It is effective for the polymerization of styrene The peroxy ketal peroxide is also widely used in butadiene rubber as crosslinking agent. It can be used as heat curing agent for unsaturated polyester.

#### Packaging and storage

25 kg PE jerrycan.

Stored below 25<sup>o</sup>C , under shadow and good air circulation .An air condition environment is recommended .