

Aceox[®] CH70S *PRODUCT DATA SHEET* 1,1-Di(tertial butyl peroxy)cyclohexane


Issued Date: 2007/09/20

Description

Aceox CH70S is a 70% 1,1-Di(t-butyl peroxy) cyclohexane in iso paraffin hydrocarbon

solvent . It is a low volatility , yellowish liquid , peroxyketal peroxide

Chemical structure



CAS No. / 3006-86-8

MW / 260.4

Specifications

Typical property	Unit	Standard
Color	Hazen-	60 max
Assay	%	70.0 ~ 71.0
Active oxygen	%	8.61 ~ 8.73
Fe	%	0.0003 max

Application

It is used as initiator of styrene polymerization . It gives a high rate of polymerization and a

low residual styrene content .

Packaging and storage

25 kgs PE jerrycan.

stored below 25[°]C , under shadow and good air circulation .An air condition environment is recommended .