



4F.-2,No. 146, Wunsing Rd., Gueishan Township , Taoyuan County 333, Taiwan R.O.C. TEL : 886-3-327-1656 FAX : 886-3-327-0223

Aceox° 101 M50

PRODUCT DATA SHEET

2,5-Dimethyl-2,5-di(butyl peroxy)hexane

Issued Date 2016/11/07

Description

ACEOX 101 M50 is light transparent resin and dialkyl peroxide with EVA and Silica.

Chemical structure

CAS No. / 78-63-7

MW / 290.4

Specifications

Typical Properties	Unit	Standard
Appearance		Light transparent chip
Assay	%	49-51
Active oxygen	%	4.57-5.57

Applications

- ACEOX 101 M50 is application for crosslinking of elastomers (EVA, PE, EPDM, Silicon rubber, NBR etc.)
- It's no benzene that product without Acetophenone and no blooming.
- Good efficient and crosslinking.

Packaging and storage

- 25 Kg paper carton. (in side plastics bag)
- Keep away from heat and sources of ignition & the best storage temperature is below 38°C.
- Keep Sealing up tightly and storing in a dry place & a well-ventilated environment. Store in well-insulated area.